

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (Currently Amended) A latent-elasticity interlaced-textured yarn, comprising:
one ply of latent-crimp conjugated yarn of 20 to 300 denier, wherein the yarn includes a composite filament which includes two kinds of polymers having different thermal shrinkages and which has a ~~monofilament~~ composite filament fineness of 1 –6 denier; and

one or two plies of ultrafine yarn of 30-300 denier having a monofilament fineness of 0.01 – 0.5 denier after a weight loss process or ~~[[a]]~~ an alkaline solvent treatment process, or after production through a direct spinning process and which are interlaced with said latent-crimp conjugated yarn using air under pressure.

2. (Previously Presented) The latent-elasticity interlaced-textured yarn as set forth in claim 1, wherein the latent-crimped yarn comprises side-by-side composite filaments having two kinds of polymers including polyethylene terephthalate and polytrimethylene terephthalate.

3. (Previously Presented) The latent-elasticity interlaced-textured yarn as set forth in claim 1, wherein the ultrafine yarn is selected from the group consisting of sea-island composite filaments, radial composite filaments and a very fine yarn produced through a direct spinning process.

4. (Previously Presented) The latent-elasticity interlaced-textured yarn as set forth in claim 1, wherein a latent-crimped yarn content is 11 to 67 wt% based on a weight of the ultrafine yarn.

5. (Previously Presented) An elastic suede-like woven fabric with elongation of 10 to 40 % and elongation recovery of 80 % or more, comprising the latent-elasticity interlaced-textured yarn as sent forth in claim 1.

6. (Previously Presented) An elastic suede-like woven fabric with elongation of 10 to 40 % and elongation recovery of 80 % or more, comprising the latent-elasticity interlaced-textured yarn as sent forth in claim 2.

7. (Previously Presented) An elastic suede-like woven fabric with elongation of 10 to 40 % and elongation recovery of 80 % or more, comprising the latent-elasticity interlaced-textured yarn as sent forth in claim 3.

8. (Previously Presented) An elastic suede-like woven fabric with elongation of 10 to 40 % and elongation recovery of 80 % or more, comprising the latent-elasticity interlaced-textured yarn as sent forth in claim 4.